

Associated Paint, Inc.



40-540.01

Pigmented Masonry Sealer Data Sheet

<u>Characteristics:</u>	<u>Specifications</u>	<u>Surface Preparation</u>
<p>Pigmented Sealer is fast drying penetrating sealer designed to seal exterior chalky concrete and masonry prior to painting. Pigmented Sealer is also recommended on bare, porous concrete and masonry to prevent absorption of the finish coat. Pigmented Sealer's coverage is excellent for surfaces where a color change is being made.</p> <p>Vehicle Type: Chlorinated Rubber</p> <p>FINISH: Low Luster</p> <p>RECOMMENDED USES:</p> <ul style="list-style-type: none"> • Exterior Cement • Porous Cement • Masonry Surfaces • Chalky Cement <p>TINTING: Not Recommended</p> <p>THINNING: Pigmented Sealer may be thinned with mineral spirits as needed. A properly sealed surface will show a slight angular sheen and will be chalk free when wiped with the hand. Test a small area with Pigmented Sealer reduced with 1 quart of mineral spirits per gallon. Allow to dry. Check to see if surface is properly sealed. Too high an angular sheen, reduce with more mineral spirits. Still chalky on surface, use less or no mineral spirits.</p>	<p>DRYING TIME, @ 77° F, 50% RH: Temperature & Humidity Dependent</p> <p>Touch: 1 hour Recoat: 10 - 12 hours Flash Point: 104° F</p> <p>VOC: <450 g/l</p> <p>Weight Solids: 60.7 ± 2% Volume Solids: 35.5 ± 2% Weight Per Gallon: 10.6 Lbs</p> <p>COVERAGE: Apply 40-540 at a rate of 300-350 sq. ft. per gallon.</p> <p>Wet Mils: 4 Mils Dry: 1.5 Mils</p> <p>APPLICATION: Apply 40-540 by brush, roller or low pressure spray. (1800-2000PSI and .017 to .019 tip).</p>	<p>Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with ((41-600TG Hot Stucco Masonry Primer)).</p> <p>Mildew Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the mildewed area for 10 minutes. Rinse thoroughly with water and allow the surface to dry prior to painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach water solution.</p>
	<p style="text-align: center;"><u>Cleanup Information</u></p> <p>Clean spills, spatters, hands and tools immediately after use with mineral spirits. Follow manufacturer's safety recommendations when using mineral Sprits.</p>	<p>Warning! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse affects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p>