

# Associated Paint, Inc.



## 40-560.01 Chalky Wall Sealer Premix Data Sheet

<u>Characteristics:</u>	<u>Specifications</u>	<u>Surface Preparation</u>
<p>Chalky Wall Sealer Premix is an alkyd sealer designed to penetrate and seal chalky and bare, porous concrete and masonry surfaces. Premix Sealer is ready for use, already reduced with solvent, eliminating the need for on the job mixing. Premix Sealer is for lightly chalked surfaces. For a more concentrated sealer see 40-500.</p> <p><b>Vehicle Type:</b> Alkyd</p> <p><b>FINISH:</b> Low Luster</p> <p><b>RECOMMENDED USES:</b></p> <ul style="list-style-type: none"> <li>• Exterior Cement</li> <li>• Porous Cement</li> <li>• Masonry Surfaces</li> <li>• Chalky Cement</li> </ul> <p><b>NOTE:</b> To be sure the surface is properly sealed, test a small area by applying 1 coat of Premix Sealer and allow to dry. A properly sealed surface will have a slight angular sheen and will be free of chalk when wiped with the hand. If not, a second coat of sealer is needed.</p>	<p><b>TINTING:</b> None</p> <p><b>THINNING:</b> None, ready for use</p> <p><b>DRYING TIME, @ 77° F, 50% RH:</b> Temperature &amp; Humidity Dependent</p> <p><b>Touch:</b> 4 to 6 hours  <b>Recoat:</b> 24 hours  <b>Flash Point:</b> 104° F</p> <p><b>VOC:</b> &lt;700 g/l</p> <p><b>Weight Solids:</b> 16.8 ± 2%  <b>Volume Solids:</b> 12.8 ± 2%  <b>Weight Per Gallon:</b> 6.8 Lbs</p> <p><b>COVERAGE:</b> Apply 40-560 at a rate of 200-250 sq. ft. per gallon.</p> <p><b>APPLICATION:</b> Apply 40-560 by brush, roller or low pressure spray. (1800-2000PSI and .017 tip).</p> <p style="text-align: center;"><b><u>Cleanup Information</u></b></p> <p>Clean spills, spatters, hands and tools immediately after use with mineral spirits. Follow manufacturer's safety recommendations when using mineral Sprits.</p>	<p><b>Masonry, Concrete, Cement, Block</b>  All new surfaces must be cured according to the supplier's recommendations usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with <b>(41-600TG Hot Stucco Masonry Primer)</b>.</p> <p><b>Mildew</b>  Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the mildewed area for 10 minutes. Rinse thoroughly with water and allow the surface to dry prior to painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach water solution.</p> <p><b>Warning!</b> Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse affects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p>